BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Date: 13-07-2015

TABLE 12 :

SL No	Test conducted	Sample No	Results	Requirements as per IS:383-1970 & Test Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2007)
1	Flakiness & Elongation Index	01	**25.30%**	Not more than 30 %
2	Impact Value	----,,----	**25.10%**	Not more then 24.00 % for BC Not more then 27.00 % for DBM Not more then 30.00 % for BM/WMM
3	Water absorption	----,,----	**0.42%**	Not more than 1.0 %
4	Stripping test. (Coating and stripping of Bitumen aggregate mixtures)	----,,----	**97.30%**	Minimum retained coating 95.0 %

*As Furnished by Client

The Results relate only to the items tested.

DEPARTMENT OF CIVIL ENGINEERING BANGALORE UNIVERSITY

Dr. MANJESH .L
ME(Civil Engg.) Ph.D. MISTE, MIRC
Associate Professor
Department of Civil Engineering
Bangalore University, Jnanabharathi Campus,
BANGALORE 560 055.
E-mail: manieshl@yahoo.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Date: 04-07-2015

TABLE 12 :

SL No	Test conducted	Sample No	Results	Requirements as per IS:383-1970 & Test Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2007)
1	Flakiness & Elongation Index	01	**23.80%**	Not more than 30 %
2	Impact Value	----,,----	**25.10%**	Not more then 24.00 % for BC Not more then 27.00 % for DBM Not more then 30.00 % for BM/WMM

*As Furnished by Client

The Results relate only to the items tested.

4/7/2015

DEPT OF CIVIL ENGINEERING BANGALORE UNIVERSITY

Dr. MANJESH .L
ME(Civil Engg.) Ph.D., MISTE, MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus,
BANGALORE 560 056.
E-mail: manjesh@yahoo.com